



US005198236A

United States Patent [19][11] **Patent Number:** **5,198,236****Gunderson et al.**[45] **Date of Patent:** **Mar. 30, 1993****[54] APPARATUS FOR FORMING STRUCTURAL COMPONENTS FROM DRY WOOD FIBER FURNISH****[75] Inventors:** **Dennis E. Gunderson, Madison;**
Roland L. Gleisner, Jefferson, both of
Wis.**[73] Assignee:** **The United States of America as**
represented by the Secretary of
Agriculture, Washington, D.C.**[21] Appl. No.:** **675,979****[22] Filed:** **Mar. 25, 1991****[51] Int. Cl.⁵ B27N 3/08****[52] U.S. Cl. 425/80.1; 162/396;**
162/400; 162/405; 162/406; 264/119; 264/120;
264/121; 425/DIG. 119**[58] Field of Search 264/86, 87, 109, 119,**
264/120, 121, 124; 425/80.1, 81.1, 82.1, 84, 85,
DIG. 119; 162/396, 400, 405, 406**[56] References Cited****U.S. PATENT DOCUMENTS**2,257,112 9/1941 Forster 65/4.1
2,725,601 12/1955 Brenner 425/80.13,177,275 4/1965 Brenner 264/517
3,428,518 2/1969 Schofer 428/378
3,939,240 2/1976 Savich 264/517
4,289,793 9/1981 Gustafson et al. 425/84
4,592,708 6/1986 Feist et al. 425/80.1
4,624,819 11/1986 Hartag et al. 264/510
4,666,647 5/1987 Enloe et al. 264/121
4,702,870 10/1987 Setterholm et al. 264/87
4,753,713 6/1988 Gunderson 162/383
4,859,388 8/1989 Peterson et al. 264/121*Primary Examiner*—Jay H. Woo*Assistant Examiner*—James P. Mackey*Attorney, Agent, or Firm*—M. Howard Silverstein; John
D. Fado; Janet I. Stockhausen**[57] ABSTRACT**

An improved apparatus for dry forming adhesive coated wood fibers in an airstream in a particular mold apparatus. The invention permits the manufacture of a mat of differing cross-sectional shapes but of uniform density. The invention includes the advantageous steps of final curing of the mat off of the main molding apparatus, thus achieving efficiencies in use.


8 Claims, 13 Drawing Sheets

Figure 1




Figure 2




Figure 3




Figure 4




Figure 5




Figure 6




Figure 7




Figure 8




Figure 9




Figure 10




Figure 11




Figure 12




Figure 13




Figure 14





Figure 15



APPARATUS FOR FORMING STRUCTURAL COMPONENTS FROM DRY WOOD FIBER FURNISH

FIELD OF THE INVENTION

This invention relates to the production of structural components from dry wood fiber using an air or vacuum deposition technique. The invention pertains to apparatus for producing such components having a non-uniform cross-sectional area, but a uniform density throughout.

BACKGROUND OF THE INVENTION

The present invention pertains to forest products and particularly to the use of wood fibers.

Trees in the USA are of two general types for commercial purposes, hardwoods and softwoods. The softwoods are well utilized for the manufacture of newsprint, paper and the like paper products. Hardwoods, in the larger trees, are well utilized for the production of lumber.

However, the hardwood category also includes large numbers of relatively small trees, trees that are deformed or are otherwise not well shaped to produce commercial sizes and quantities of lumber, and the relatively larger as well as the smaller limbs of the larger hardwood trees which are not utilizable for lumber. The present invention is directed towards utilization of this resource.

That is, softwood production is well spoken for and most of the hardwood production is spoken for. It is the part of the hardwood production which is not otherwise usable at present which is usable in accordance with the invention to produce structural material such as panels with texturized surfaces and other objects of a particular category.

The prior art has been aware of certain problems in the use of hardwood fiber in methods such as the present invention that involve pressing of the fibers into products. Hardwoods tend to have short and thick walled fibers. These short thick walled fibers, when used in conventional processes of the same general category as the present invention and in paper making, tend to bond to each other only poorly, and, especially important as to paper, tend to exhibit poor tear strength and an abundance of natural and generated fine material that causes drainage problems resulting in low wet web strength. In the present state of the art, hardwood pulps are used primarily only as a filler and as a means to provide smoother surfaces on paper for printing.

Because of these problems, utilization of hardwoods of lower than lumber quality as set forth above has not occurred. This results in a good deal of waste of these lower quality hardwoods resulting in added pressure on softwood production.

In the prior art of the utilization of such wood fiber, the techniques utilized basically fall into two categories, using the fibers when they are wet, and using them when they are dry. The present invention is a dry or air as opposed to water deposition type of process.

The invention uses bonding techniques to form the final structural members. Wet techniques tend to be slower, involve many steps including those to drain the water used for the forming and to dry. These steps are all avoided with dry forming techniques such as the present invention.

Finally as to the prior art, attention is invited to two earlier patents, U.S. Pat. No. 4,702,870 issued Oct. 27, 1987 to Setterholm and Hunt; and U.S. Pat. No. 4,753,713 issued Jun. 28, 1988 to the present inventor, Dennis Gunderson. Both of these patents are owned by the U.S. Government, Secretary of Agriculture on behalf of the U.S. Forest Service.

Gunderson U.S. Pat. No. 4,753,713 teaches forming of a uniform density mat by draining a fiber bearing slurry through porous mandrels, and subsequent consolidation of the web in the mold. In U.S. Pat. No. 4,702,870, Setterholm and Hunt teach the wet-forming of a mat of variable cross-section on a support of resilient deformable mold inserts or "nubs" on a forming wire. They show how the web can be molded directly on the nubs and then consolidated as web and resilient inserts are pressed together under pressure applied normal to the surface of the web.

The present invention distinguishes from U.S. Pat. No. 4,753,713 in that: (1) the present invention is an air-forming and not a wet-forming method, (2) the present invention is not limited to drying on the mold, but provides means to remove the web from the mold and complete consolidation and cure thereof remote from the porous mandrels. The present invention distinguishes from Setterholm and Hunt in U.S. Pat. No. 4,702,870 in that the web is not formed on the resilient deformable blocks as taught by them--nor is it wet formed. Further, in the present invention, it is the protrusions in the forming apparatus which are porous whereas in Setterholm and Hunt it is the base material which is porous. In the present invention, there is significant one-dimensional (thickness direction) consolidation of the web on the mandrels. This is very significant because it permits the forming of much deeper sections (greater variations in cross-section) than is possible with the methods taught by Setterholm and Hunt. Moreover, the present invention teaches means to achieve further one-dimensional consolidation of the web even after the resilient pillows have been inserted in the web. The withdrawal of the solid block into the support plate (one-dimensional consolidation) prior to the distortion of the resilient pillows (three-dimensional consolidation) is not taught by Setterholm and Hunt.

A dry formed web cannot be adequately consolidated in the forming apparatus and the means to proceed with further consolidation and curing are not obvious from these prior patents. The present invention teaches a novel means to contain and support the web when the forming mandrel is withdrawn. Further, the invention teaches a novel means to proceed with consolidation of the web after it is removed from the mandrels.

SUMMARY AND ADVANTAGES OF THE INVENTION

The present invention provides means to produce sculptured structural fiberboard products using a mold that includes porous forming areas that in one embodiment are porous mandrels movably mounted in the mold. Forming is done with adhesive-coated, dry wood fibers carried by air. The thick, low density mat of fibers so deposited by the air is consolidated to form a sculptured mat of uniform high density. Final densification of the mat and activation of the adhesive is performed off the mold, i.e., not on the mandrels, in a manner which lends itself to mass production processes.

The invention provides such a method for making such products using a dry forming technique, thus

avoiding all of the problems and disadvantages in wet forming techniques.

In an alternative embodiment, the present invention teaches further novel means to integrate the rigid blocks and resilient pillows with the retractable porous mandrels in a way that reduces the number of separate operations and handling required in the process. This embodiment is also advantageous in that it provides support to that portion of the web which is most susceptible to "springback" when the mandrels are withdrawn.

The invention manifests itself in a particular sequence of steps to produce such products and to achieve these advantages. These steps are:

1. A first vacuum deposit of relatively small amount of fiber.

2. Pressure on that first deposit including opening the vacuum head of the special machine to perform this step.

3. A second vacuum deposit of the remaining fiber.

4. Pressing on that, combined with retracting the porous mandrels to get the main compression, this step being performed with an atmospheric pressure assist due to the further application of vacuum pressure.

5. Removal of the frame with the compressed mat thereon. The main equipment is thus released to repeat steps 1-4, while the remaining steps summarized in 6 following are performed off the main equipment.

6. Using pillows, blocks, more pressure, and heat to produce the final product, off of the main mold.

Another feature of the invention is the coordination of the movement of the platen and the mandrels in such a way as to compress the face and the ribs of the product being produced to the same level of compression. This will produce the desired sculptured product having varying cross-sectional sizes but having the same density throughout.

Thus, an important advantage of the invention overall is the use of a dry technique to produce structural members from dry wood fibers having non-uniform cross-sections, but uniform density.

Another advantageous feature of the invention is the means to provide coordinated movement of the mandrels and the pressing platen in such a way as to produce the above described new product.

Another advantage of the invention is the apparatus of removing the web from the mold while it is contained in relatively low cost parts. This permits final densification and curing of the web in low cost components, while releasing the remaining main portions of the mold to produce new webs.

Another advantage of the invention is its use of particular elastic pillows and rigid blocks to produce this uniform densification with dis-uniform cross-sectional shapes in a dry forming technique.

Finally, the invention accomplishes the above by the provision of a particular combination of steps in its method.

Thus, in summary, there is provided an important step forward in this art, wherein a contoured or sculptured mat of varying cross-sections is air or vacuum formed using pretreated dry fiber furnish. It is believed that such a process has been heretofore unknown in the prior art.

BRIEF DESCRIPTION OF THE DRAWINGS

This invention will be more clearly understood with reference to the accompanying drawings, which drawings also form a part of this disclosure, and wherein:

FIGS. 1-10 are a sequence of schematic drawings which illustrate the primary method of the invention;

FIG. 11 is a schematic drawing which illustrates a second embodiment;

FIG. 12 illustrates an underlying concept used in the invention;

FIG. 13 is a diagram illustrating the manner of operation of certain portions of the invention;

FIG. 14 is a showing of a product produced in accordance with the invention; and

FIG. 15 is a showing of a detail.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

In FIG. 1 there is shown a molding apparatus means 100 according to the invention comprising removable rigid porous mandrel means 1, removable perforated plate means 2, frame 3, base 4, and elevator assembly 5 at a forming station also comprising sideboard 6 and forming hood 7. The mandrels 1 may be one or greater than one in number and may be made of sintered bronze. A vacuum drawn at port 8 in the base 4 causes air to be drawn in at port 9, into hood 7, and thence through the porous mandrel means 1 into the interior of base 4. Fiber entering port 9 carried by the air flow is deposited on the surfaces of the partially retracted mandrel means 1 so as to fill the spaces between the mandrels, as shown.

A fundamental problem in creating a deeply sculptured dryformed panel or the like as is done with the present invention is that of depositing enough fiber into the rib sections. Because air laid mats tend to be of very low density prior to compaction, an air formed mat of fibers may be from five to ten times thicker than the thickness of the finished, compacted, cured panel. In the case where one is attempting to form a narrow rib structure, the problem is especially difficult because the deep mat of fiber must be formed in the narrow gaps between mandrels. The natural tendency of the dry wood fiber is to cling together, thus bridging the space between the mandrels rather than be drawn into it in sufficient quantity. The greater the fiber length, the greater the tendency to "cling" and "bridge". The process steps illustrated in FIGS. 1, 2, and 3 overcome this difficulty and allow the invention to form (deposit) as much fiber as desired in the ribs.

The process depicted in FIGS. 1-3 is a simplification in two ways: (1) the mandrels may in fact be raised in several steps with compaction of the web prior to each raising of the mandrels, and (2) the removable rib compacting grid means 10 would in practice be preferably located within the hood 7. It is not difficult to envision in FIG. 3, for example, that the top of the hood 7 could be higher than shown to accommodate the removable rib compacting grid means 10 and a suitable actuator without interfering with the forming process. In such a configuration, several steps of fiber deposition, compaction and raising of the mandrels could be conveniently implemented without removing the forming hood 7.

Note that the fingers 10A of the removable rib compacting grid means 10 need not be fit tight between the mandrels to be effective. Here the tendency of the fibers to cling and form a network is an advantage. The fiber being compacted does not try to escape through the clearance spaces between the compacting grid "fingers" and the mandrels due to this cling tendency.

The advantage of the two-step or multi-step fill and compact process of this invention is that it gets an ade-

quate quantity of fiber into otherwise very difficult to form sections. Because the depth of the section formed at any one time in the process is relatively small, the invention gets uniform, even, dependable distribution of fiber in the rib sections. The invention also greatly reduces the potential for a void somewhere in the rib caused by bridging, a condition which would likely be cause for rejection of the final panel. Finally, this part of the method of the invention makes possible the formation of very deep sections, which would not be possible using an array of stationary mandrels.

In FIG. 2, the forming hood 7 has been removed to provide access to the mandrel means 1 and a removable rib compacting grid means 10 has been positioned over the mandrels. The removable rib compacting grid means need fit only loosely into the spaces between the mandrels because the fibers naturally tend to cling together even when dry, as discussed above. When pushed into these spaces, the grid compacts the low density web of fibers pictured in FIG. 1 to the condition shown in FIG. 2, which is the first compaction step according to the invention. Multiple such "first" compaction steps are also possible, as discussed herein.

In FIG. 3 the forming hood 7 is again positioned over the sideboards 6. The elevator assembly 5 has been raised to fully project the mandrels into the chamber defined by the frame 3 and sideboards 6. A vacuum is drawn at port 8 in the base 4 to cause more air and fiber to enter port 9 in the forming hood 7. This added fiber is deposited in a low density mat between, potentially and over the tops of, the porous mandrel means 1, and on top of the partially compacted fibers, as shown. This is the "second" vacuum deposition step according to the invention.

In FIG. 4 the forming hood 7 has been again removed and a flat platen means 11 has been placed on the fiber mat within the confines of the sideboard 6.

FIG. 5 depicts the initial consolidation of the air-formed low density fiber structure. The platen means 11 is forced downward, as shown by the large arrow F, and the mandrel means 1 are withdrawn through the perforated plate 2 by action of the elevator assembly 5. The volume of the fiber web contained by the perforated plate 2, frame 3, and platen means 11 is reduced and its density, therefore, increased. The downward force required to compact the web (represented by arrow F in FIG. 5) may be imposed by an actuator external to the mold assembly.

Alternatively, an effective web consolidation force of 10-12 psi can be achieved by drawing vacuum at port 8 via the porous mandrels. When the apparatus is operated in this mode, platen means 11 must be fitted with a removable, sliding seal 17, to prevent air leakage in the clearance spaces between platen means 11 and frame 3 and sideboard 6. The seal 17 must prevent air leakage and also slide easily along the sideboard 6 and frame 3 as the platen means moves downward. With a vacuum at port 8, atmospheric pressure on platen means 11 applies a uniform compaction force on the web.

In FIG. 6, the initial consolidation of the web is complete. Platen means 11 is temporarily locked to frame 3 by locking means 16 and mandrel means 1 have been fully retracted from the web. At this time, the web has been compressed in the vertical direction only. Examining FIGS. 4, 5, and 6, it is apparent that the combined effect of the platen and mandrel movements is to compress both the area between the mandrels and the area over the top of the mandrels. By so coordinating the

platen and mandrel movements, it is possible to compress the face and ribs at the same compression ratio.

Platen means 11 is temporarily locked to frame 3 by locking means 16. Mandrel means 1 have been fully retracted from the web. The locking means 16 are inserted through a hole in frame 3 and into associated holes in platen means 11 when the web has been compressed to the proper thickness. Because the fiber tends to spring back upon removal of the compressing force F, it is necessary to so lock platen means 11 to frame 3 to maintain the fiber mat in a compressed state.

Knowing that a dry compressed mat of fibers will tend to expand (springback) if the compressing force is relieved, it should be apparent in FIG. 6 that the portion of the web formed over the top of the mandrel will tend to spring back when the mandrels are withdrawn. This tendency to spring back limits the extent of compression which can be accomplished prior to removal of the mandrels. If the web is fully compressed prior to removal of the mandrels, the portion over the mandrel will spring back and disrupt the integrity of the web when the mandrel is withdrawn.

Examining FIGS. 4 and 5, it is apparent that the combined effect of the movement of the platen means 11 and the mandrel means 1 is to compress both the area between the mandrel means 1 (i.e. the ribs of the final panel) and the area over the top of the mandrels (facing).

This aspect of the invention is illustrated in more detail in FIG. 12 wherein the platen, mandrel and dry furnish are depicted in initial and partially compacted states.

The height of the rib is shown to be initially m and subsequent m' . Rib compaction ratio is, therefore m/m' . Facing thickness is initially $1-m$ and subsequently $1'-m'$. Facing compaction ratio is, therefore $1-m/1'-m'$. The relative compaction of rib to facing may be expressed as follows:

$$k = \frac{m/m'}{1 - m/1' - m'} \quad \text{or} \quad k = \frac{1'm - mm'}{1m' - mm'}$$

If rib and facing are equally compacted, $k=1.0$. If the ribs are to be more densely compacted than the facing, then $k>1.0$. If the facing is to be more dense than the ribs, then $k<1.0$. The means by which the displacements of platen and mandrel are controlled to achieve desired compaction ratios is schematically illustrated in FIG. 13.

Referring to FIG. 13, displacement sensors monitor the initial and all subsequent positions of the platen means 11 and mandrel means 1 relative to the perforated plate 2. Initial values of (1) and (m) are stored for subsequent computation of the rib to face compaction ratio (k) as the consolidation process begins. While the platen is lowered at a constant rate by the fixed rate platen drive, values of $1'$ and m' are used by the controller 30 to compute a (k) values which is then compared with the value specified by the operator.

The controller 30 repeatedly directs the variable speed mandrel drive 32 to adjust the rate of mandrel retraction (thereby adjusting the m' value) to achieve the desired k value—i.e., the desired relative compaction of rib and face sections.

FIG. 7 shows how the web is next removed from the mold for further densification and curing. Platen means 11 is locked to frame 3 by locking means 16. Frame 3 is affixed to perforated plate 2 by screws 28. It is thus

possible to lift the pressing assembly comprising these mold components and the consolidated web from the mold. This leaves the main machinery available to form more mats using another set of the simpler, parts including plate 2, frame 3 and sideboard 6 and hood 7. The invention thus has the further benefit of maintaining continuous control, restraint, and support of the as yet not cured mat or web from the time when it is formed until it is fully cured.

FIGS. 8, 9 and 10 show how the partially formed web is then further densified and its adhesive cured, all of which is done off of the mold.

In FIG. 8, silicone rubber pillows 12 and rigid blocks 13 have been inserted into each of the "pockets" or cavities which had been created by the forming mandrel means 1 in FIG. 5, and which were subsequently vacated when the mandrels were withdrawn as shown in FIG. 6. Each pillow 12 and block 13 is inserted into the web through the corresponding hole which exists in the perforated plate 2. Plate 2 is shown in cross-section to show the mandrel holes. A slight interference between the web and both pillow and block hold the pillows and blocks in place.

In FIG. 9, a further consolidating force F , is being applied to platen means 11 while the perforated plate 2 is firmly supported on a suitable support surface 23 or the like. The locking means 16 which held platen means 11 in frame 3 have been released. FIG. 9 illustrates that during this phase, the force applied to the platen means 11 and the resulting further consolidation of the web have caused the rigid blocks 13 to move downward out of the fiber web, and into the corresponding holes in perforated plate 2. The rigid blocks 13 then rest upon the same support surface 23 as the perforated plate 2.

In FIG. 10, a still greater consolidating force F'' is applied to platen means 11. In this step, the silicone rubber pillows 12 deform so as to create essentially equal pressure in all directions throughout the web. Depending on the force applied, and the particular furnish used, densities from 0.6–1.0 g/cm³ can be practically achieved throughout the web. At this stage, the temperature of the web is raised by heat conducted from heater 24 through the platen means 11 and perforated plate 2. Heater 24 could be electric, hot air or steam heated. Typically, the temperature of the platen means 11 and perforated plate 2 would be raised to about 325°–375° F. for about 10 minutes to cure the adhesive resin previously applied to the wood fibers. When the adhesive resin applied to the fibers has cured, the force F'' can be removed and the panel withdrawn from the frame 3. A typical finished product is shown in FIG. 14. The web will retain the shape and density achieved during the pressing and curing process. Silicone rubber pillows 12 will revert to their original shape and can be easily removed from the panel—to be used again in fabrication of additional panels.

Use of the deformable rubber pillows for the final compression stage follows the concepts taught in the Setterholm and Hunt U.S. Pat. No. 4,702,870. The function is the same as that shown in FIGS. 3–8 of that patent.

The invention requires a different approach, however, because the deep section of dry formed webs cannot be formed on the rubber mold inserts, as is described herein.

The invention forms the mat on the porous mandrels 1 and partially compacts the web as in FIGS. 4 and 5. The invention removes the mandrels at this point and

inserts the rubber pillow and a solid block into each mandrel cavity. The block provides an additional "stage" of vertical compaction of the face and ribs before the pillows begin to deform. This step is essential. If the web is compacted too much before the mandrel is removed (ref. FIGS. 4 and 5), the compressed (but as yet unbonded) ribs will (under the force of stored, internal, compressive energy) distort and collapse when the mandrels are removed (FIG. 6). Yet, if the web is not sufficiently well compacted at the time the rubber pillows begin to deform, there will be excessive distortion of the pillows and the ribs will be distorted and/or poorly compacted. The two-step process of FIGS. 8–10 provides the needed first step of rib compression (without pillow distortion) as the blocks slide into place in the recesses of plate 2 followed by the high pressure final compaction and curing of FIG. 10. The combined functioning of sliding block and subsequent pillow compression provide the essential functions of secondary rib compression (with integral support in place), and final pillow compaction.

FIG. 11 depicts an alternate configuration in which the silicone rubber pillows 12 and blocks 13 of FIG. 8 are made as a separable component part of the porous mandrels 1 of FIGS. 1–10. In this alternate design, a porous segment 15 and silicone rubber pillow 12 are part of the forming mandrel. These components are left in the web when the forming mandrels are withdrawn. This arrangement eliminates the operations necessary to insert the silicone rubber pillow 12 and rigid block 13 into the web as depicted in FIG. 8 and described above. FIG. 11 shows the elevator assembly 5 of FIGS. 1–10 in a fully retracted position within the base 4. A moveable rigid porous mandrel 14 is shown in lieu of porous mandrel 1 of FIGS. 1–10. The phantom lines above the mandrel 14 indicate where the porous segment 15 and silicone rubber pillow 12 would be positioned during the web forming phase.

Referring to FIG. 15, a detailed drawing of the mandrel 14 of FIG. 11, the means by which this can be accomplished is shown. The truncated mandrel 14 and porous segment 15 can be made of the same porous material. A ridge 14A on the top of the truncated porous mandrel 14 engages a corresponding recess not shown in the bottom of the segment 15. Parts 14 and 15 thus mate or engage so that their four sides are aligned and they cannot rotate with respect to one another about a vertical axis. The pillow 12 is molded to shape and permanently bonded to the top surface of segment 15 as by a suitable adhesive. Comparing FIG. 11 with FIG. 7, note that the rib sections which are entirely without lateral support in FIG. 7 are supported by the segment 15 and pillow 12 in FIG. 11.

The pillow/block assembly 12, 15 need not be mechanically attached or fastened to the truncated porous mandrel 14 during either the forming or compaction procedure. During the web compaction process, it will be pushed onto the top of the mandrel by the force of the descending platen means 11. However, once the compaction process is over (at FIG. 5, for example), the assembly 12, 15 will be left in the web as the mandrel is fully withdrawn. Because the segment 15 (referring to FIG. 15) is of the same porous material as the truncated porous mandrel 14, the only loss to porous flow is that relatively small surface area comprising the surface of the pillow. Loss of vacuum surface here is relatively insignificant because the upper surface (face) is the easiest to form.

This configuration of components expedites processing and reduces handling the molded web. The pillow and segment are thus inserted in the web as it is being formed, thus eliminating the need for retraction of the whole mandrel and subsequent reinsertion of block 13 and pillow 12. This configuration has the further advantage of providing additional support to the loosely consolidated web structure—reducing the “springback,” which occurs when the whole mandrel is removed.

FIG. 11 corresponds to FIG. 7 wherein the web is removed from the mold for final densification and curing. Platen means 11 is locked to frame 3 and frame 3 is affixed to perforated plate 2, both as in the first embodiment. The pressing assembly comprising platen means 11, frame 3, plate 2 and the web, is removed from the mold as in FIG. 7. In FIG. 11, however, the rigid and elastic components 15 and 12 respectively, are retained in the assembly and the web can go directly to the pressing operations shown in FIGS. 9 and 10.

The pillow and block combination together support the loosely consolidated web during the consolidation shown in FIGS. 9 and 10. In this step, there is “one-dimensional” consolidation in the thickness direction only. As the web sections between the pillows and blocks compress, the blocks move into the corresponding voids in the perforated plate—accommodating the consolidation of the web without distortion of the elastic pillows. Once the blocks are fully positioned and receded into the corresponding spaces in the perforated plate, they provide the supporting surface for final densification of the web depicted in FIG. 10.

A significant benefit of the invention as shown at FIGS. 7 and 11 is that once the web is formed and initially compressed, plate 2, frame 3, and platen means 11 are removed. The remainder of the forming assembly can be fitted with a new plate 2, frame 3, and platen means 11 to start the forming process once again. Thus, the major portion of the apparatus (mandrel means 1, base 4, elevator assembly 5, sideboard 6, and forming hood 7) can be used again and again to mold more sculptured webs, while already formed webs receive final pressing and heat curing of the adhesive, off of the main molding apparatus.

While the invention has been described in some detail above, it is to be understood that this detailed description is by way of example only, and the protection granted is to be limited only by the spirit of the invention and the scope of the following claims.

We claim:

1. Apparatus for forming a product of pretreated wood fiber from a mat of air-laid wood fiber, said product having non-uniform cross-sectional shapes and a substantially uniform density, comprising molding apparatus means, movable rigid porous mandrel means operatively associated within said molding apparatus means having at least one mandrel, means to mount said mandrel means within said molding apparatus means, removable perforated plate means operatively associated within said molding apparatus means, means to

mount said plate means in said molding apparatus means so that said mandrel means may move through openings in said plate means, frame means mounted to said plate means, removable rib compacting grid means operatively associated with said mandrel means, means to flow air through said molding apparatus means and said mandrel means, means to supply said wood fiber in a dry condition into said air flow to cause said wood fibers to deposit in spaces around said mandrel means on said plate means while said mandrel means are in a first position in said molding apparatus means, platen means for compacting said deposited wood fiber to form a mat, said frame means, said plate means and said platen means together with said mat being removable as a unit from said molding apparatus means to allow formation of additional mats, resilient pillow means attached to rigid block means adapted to fit into cavities formed by said mandrel means in said mat, means for applying mat consolidation force onto said platen means to urge said block means into the corresponding openings in said plate means, means for applying increased mat consolidation force onto said platen means to cause said pillow means to deform to thereby apply substantially equal pressure in all directions throughout said mat, and means for heating said mat to cure said wood fiber.

2. The apparatus of claim 1, wherein said platen means is separate from said molding apparatus means.

3. The apparatus of claim 1, further comprising means for causing predetermined coordinated motions of said mandrel means and of said removable rib compacting grid means.

4. The apparatus of claim 1, further comprising means for positioning said removable plate means in said molding apparatus means so as to divide said molding apparatus means into two chambers with said porous mandrel means movably mounted in one of said chambers in said molding apparatus means so as to extend through said openings in said plate means and to thus be located in both of said chambers.

5. The apparatus of claim 1, wherein said pillow means and said rigid block means are in the form of removable ends of said mandrel means which remain in the cavities formed in said mat by said mandrel means.

6. The apparatus of claim 1, further comprising locking means for securely holding said platen means in position with respect to said frame means and said plate means.

7. The apparatus of claim 1, further comprising finger means extending towards said mandrel means from said removable rib compacting grid means, said finger means providing for additional compaction of said wood fiber around said mandrel means.

8. The apparatus of claim 7, wherein said finger means comprises a plurality of fingers for compaction of said wood fiber, and said at least one mandrel comprises a plurality of mandrels, said fingers capable of extension between said plurality of said mandrels.

* * * * *